

Independent  Textile
Testing
Service, Inc.

Test No: 146821

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722
Phone: 706-278-3013 • Fax: 706-272-7057 • E-mail: info@ittslab.com

Test Report

Customer: UPOFLOOR

August 25, 2014

Subject: One sample of vinyl floor covering submitted by the customer and identified as below.

Sample Identification: Upofloor Zero 5703
Contract Sheet
Date of Manufacturing: 25th June 2014

Test Method Conducted
ASTM F 1914 Standard Test Method for
Short-Term Indentation and Residual Indentation of Resilient Floor Covering
Re: ASTM F1913 Standard Specification for Vinyl Sheet Floor Covering without Backing

Scope:

This method covers the determination of short-term indentation and residual indentation of resilient nontextile floor coverings, such as vinyl plastic, linoleum, and felt-backed materials, when subjected to a concentrated load.

Specified Load: 75 lbs.

TEST RESULTS	
Original Thickness	0.072"
Final Thickness	0.069"
Residual Indentation	0.003"


President L. Kent Suddeth

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of Independent Textile Testing Service, Inc., must receive our prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of Independent Textile Testing Service, Inc., are not to be used under any circumstances in advertising to the general public.