



## OAK HANDBÖRD

DDODLICT DETAIL C

The cloudy stain on this single-strip oak floor from the Småland Collection allows the lightly smoked nuances in the wood to seep through, resulting in a very rustic expression. Light and dark contrasts in the wood are punctuated with occasional saw marks, which give the floor its restored appearance. Four-sided bevelling at the edges ensures a classic, full plank look and feel. Each board is meticulously hand-scraped, which enhances the rustic appearance of the floor.

PRODUCT DETAILS		PRODUCT DETA
Product type / Construction	Wood Floors / 3-layer parquet	Hardness (Brinell
Article Number / EAN Code	151NDSEK06KW240 / 7393969039079	range
Design / Wood Species	Plank / Oak	Warranty
Surface treatment /	Oil / Stained	TECHNICAL PR
Natural/Stained		— Moisture content
Design features	Bevelled 4-sided, Brushed, Light smoked,	Minimun Mean D
	Handscraped, Saw marks	— kg/m³
Width x Length x Thickness	187 x 2420 x 15 mm	— Reaction To Fire
Weight per package / per	22 kg / 8.15 kg	-
m2		Formaldehyde Er
Area per package / per	2.72 m <sup>2</sup> / 122.4 m <sup>2</sup>	Content PCP
pallet	2.72 111 7 122.4 111	Breaking Strength
	Everageive	— Thermal Conduct
Grading	Expressive	Biological Durabil
Joint	Woodloc® 5S	— CARB2
Installation method	Floating, Glue-down	— Slip resistance
Floor heating	Yes	Slip resistance
Wear leayer material /	Hardwood / 3.5 mm	TSCA
thickness		CARB P2
Resandable	2-4 times	Compliant
Core material	Pine/Spruce	

PROD	UCT L	ETAILS

Hardness (Brinell) value /	3,7 / 2.2 - 5.9
range	
Warranty	30 years

## ROPERTIES

Moisture content	EN13183	7%±2%
Minimun Mean Density		>500 kg/m³
kg/m³		
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 ppm
Breaking Strength N/mm <sup>2</sup>	EN1533	NPD
Thermal Conductivity	EN12664	0,11W/mK
Biological Durability	EN350-2	Class 1
CARB2		Compliant
Slip resistance	CEN/TS15676	NPD















## **DETAILED DESCRIPTION**

Backside material

All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood may occur.

The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

Oil: This floor should be oiled immediately after installation.

Colour change: Stained product - noticable color change over time.

Veneer

Packages may contain start and stop boards.

**Descriptions & Imagery** 

www.kahrs.com | ©Kährs

## Other products in this collection



OAK KLINTA



OAK SEVEDE



OAK YDRE



OAK MÖRE



OAK VISTA



OAK VEDBO



OAK TVETA



OAK FINNVEDEN



OAK ASPELAND