

MONT BLANC DRY BACK 0.3 MM

Our Luxury Tiles Dry Back collection is available in a wide selection of stone designs, spanning from classic stone to concrete. The Dry Back floors, with a 0.3 mm wear layer, are based on virgin vinyl and constructed in five different layers, topped by a ceramic coating. The result is extremely resilient and strong floors resistant to both scratching and water, which means that these floors are suitable even for spaces exposed to heavy traffic. Just like all our other Luxury Tiles floors, they are phthalate-free.

| PRODUCT DETAILS | | | TECHNICAL PROPERTIES | | |
|-------------------------------|--|---------------|---|--------------|------------------------|
| Product type / Construction | Luxury Vinyl Tiles and Planks / Dry Back LVT | | Statcal electrical | EN 1815 | < 2 kV (antistatic) |
| Article Number / EAN Code | LTDBS3015-457-3 / 7393969113915 | | propensity | | |
| Design | Tile Design | | Chemical resistance | EN ISO 26987 | Pass with good results |
| Width x Length x Thickness | 457 x 457 x 2.5 mm | | Effect of castor chair | EN 425 | Suitable |
| Weight per package / per m2 | 21 kg / 4.2 kg | | Resistance to bacteria and fungi | | Good |
| Area per package / per pallet | 5.01 m ² / 240.5 m ² | | <div></div> | | |
| Installation method | Glue-down | | | | |
| Floor heating | Yes | | | | |
| Wear leayer thickness | 0.3 mm | | | | |
| TECHNICAL PROPERTIES | | | | | |
| Reaction To Fire | EN13501-1 | Bfl-s1 | | | |
| Thermal Resistance R-Value | | 0.011 (m2K/W) | | | |
| Dimensional stability | EN ISO 23999 | < 0.1 % | | | |
| Colour fastness | EN ISO 105-B02 | ≥ 6 | | | |
| Slip resistance | EN 13893 | DS (>0.3) | | | |
| Slip resistance | DIN 51130 | R10 | | | |

Other products in this collection



KILIMANJARO DRY BACK



STEELE DRY BACK



SCHWARZHORN DRY BACK



MATTERHORN DRY BACK



MAKALU DRY BACK



LUCANIA DRY BACK




KEBNEKAISE DRY BACK



GROSSGLOCKNER DRY BACK




MONT BLANC DRY BACK



DOM DRY BACK



BROAD PEAK DRY BACK



LHOTSE DRY BACK