



## TAIGA DBW 229-030 - 0.3 MM

Our Luxury Tiles Dry Back collection is available in a wide selection of wood and stone designs. The wood designs range from traditional to rustic, while the stone designs span from classic stone to concrete. It also includes exciting patterns. The Dry Back floors, with a 0.55 mm wear layer, are based on virgin vinyl and constructed in five different layers, topped by a ceramic coating. The result is extremely resilient and strong floors resistant to both scratching and water, which means that these floors are suitable even for spaces exposed to heavy traffic. Just like all our other Luxury Tiles floors, they are phthalate-free.

### PRODUCT DETAILS

|   |                                 |
|---|---------------------------------|
| Construction                            | Dry back                        |
| Article Number / EAN Code               | LTDBW2115-229-3 / 7393969114103 |
| Design                                  | Wood design                     |
| Width x Length x Thickness              | 9 x 48 x 1/8"                   |
| Weight per package / per m <sup>2</sup> | 35.3 lbs / 8.8 lbs              |
| Area per package / per pallet           | 43.1 sqft / 2858.9 sqft         |
| Installation method                     | Glue-Down                       |
| Floor heating                           | Yes                             |
| Wear leayer thickness                   | 0"                              |

### TECHNICAL PROPERTIES

|                            |                |                            |
|----------------------------|----------------|----------------------------|
| Reaction To Fire           | EN13501-1      | Bfl-s1                     |
| Thermal Resistance R-Value |                | 0.011 (m <sup>2</sup> K/W) |
| Dimensional stability      | EN ISO 23999   | < 0.1 %                    |
| Colour fastness            | EN ISO 105-B02 | ≥ 6                        |
| Slip resistance            | EN 13893       | DS (>0.3)                  |
| Slip resistance            | DIN 51130      | R10                        |

### TECHNICAL PROPERTIES

|                                  |              |                        |
|----------------------------------|--------------|------------------------|
| Statical electrical propensity   | EN 1815      | < 2 kV (antistatic)    |
| Chemical resistance              | EN ISO 26987 | Pass with good results |
| Effect of castor chair           | EN 425       | Suitable               |
| Resistance to bacteria and fungi |              | Good                   |



### Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.

## Other products in this collection



Gorbea - Dry back



Stanton - Dry back



Snowdonia - Dry back



Durmitor - Dry back



Calder - Dry back



Burnham - Dry back



Tongass - Dry back



Tiveden - Dry back



Cormorant - Dry back



Yukon - Dry back



Taiga - Dry back




Sherwood - Dry back



Riva - Dry back



Niagara - Dry back



Belluno - Dry back



Wentwood - Dry back



Schwarzwald - Dry back



Saxon - Dry back



Sarek - Dry back



Redwood - Dry back



Oulanka - Dry back



Komi - Dry back



Whinfell - Dry back



Daintree - Dry back



Waipoua - Dry back



Valdivian - Dry back



Humboldt - Dry back



Plitvice - Dry back



Triglav - Dry back