



OAK NOUVEAU INK

Deep and dark tones with a warm glow underneath creates a robust and full-bodied atmosphere.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	151N9AEK19KW200	Wood Species	Oak	Moisture	EN13183	7%±2%
EAN Code	7393969046442	Design	1-strip	content		
Surface Treatment	Matt lacquer	Grading	Lively	Minimun Mean Density kg/m³ >500 kg/m³		
Refining Treatment	Brushed, Microbevelled 4-sided	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1
Dimensions	187 x 2000 mm	Collection	Classic Nouveau Collection	Formaldehyde Emission	EN717-1	E1
Weight per Package	18 kg	Natural/Stained	Stained	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Area per Package	2.2 m ²	Brinell Value	3,7	Breaking Strength N/mm²	EN1533	NPD
Area per pallet	100.8 m ²	Joint	Woodloc® 5S			
Package info	Packages may contain start and stop boards.	Floor heating	Yes			
			25 years	Thermal Conductivity	EN12664	0,14 W/mK
DETAIL DESCRIPTION		Wear-layer material	Hardwood	Thermal Resistance R-Value		.11 (m2K/W)
All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers. COLOUR CHANGE		Wear Layer Thickness	3.5 mm	Biological	EN350-2	Class 1
		Core material	Pine/Spruce lamella	Durability		
		Backside material	Spruce	CARB2		Compliant
			15 mm	Slipperiness CEN/TS15676		NPD
		Installation method	Floating, Glue-down			
Stained product - noticeable color change over time.		Surface Colour	Dark brown			

Other products in this collection



Oak Nouveau Lace



Oak Nouveau Rich



Oak Nouveau Blonde



Oak Nouveau Gray



Oak Nouveau Tawny



Oak Nouveau Greige



Oak Nouveau White



Oak Nouveau Snow



Oak Nouveau Black

CERTIFICATES









Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.