



HARD MAPLE NEBBIA

The light grey tones in this single-strip hard maple floor from the Domani Collection highlight its rustic expression. Knots and cracks pepper the boards, resulting in a beautifully aged effect reminiscent of reclaimed timber. Each board is carefully brushed to bring out the character of the grain and highlight the natural texture of the wood. Four-sided micro-bevelling at the edges ensures a classic full plank look and feel. Hand-scraping enhances the worn appearance of the floor.

DDODLICT DETAIL C

PRODUCT DETAILS		PRODUCT DETAILS	
Product type / Construction	Wood Floors / 3-layer parquet	Hardness (Brinell) value /	5 - 6
Article Number / EAN Code	151XCDAPWBKW195 / 7393969045353	range	
Design / Wood Species	1-strip / Hard maple	Warranty	30 ye
Surface treatment /	Oil / Stained	TECHNICAL PROPERTIES	
Natural/Stained		Moisture content	EN13
Design features	Microbevelled 4-sided, Brushed, Smoked,	Minimun Mean Density	LIVIS
	Handscraped	— kg/m ³	
Width x Length x Thickness	190 x 1900 x 15 mm	— Reaction To Fire	EN13
Weight per package / per	17.1 kg / 7.77 kg	Formaldehyde Emission	EN71
m2		— Content PCP	CEN/
Area per package	2.2 m ²		
Grading	Dynamic	Breaking Strength N/mm²	EN15
Joint	Woodloc® 5G	Thermal Conductivity	EN12
Installation method	Floating, Glue-down	Thermal Resistance R-Value	
Floor heating	No	Biological Durability	EN35
Wear leayer material /	Hardwood / 3.5 mm	— CARB2	
thickness		Slip resistance	CEN/
Resandable	2-3 times	BOTESSIONE DAME LIAN INTERFECE	
Core material	Spruce	CARB P2	BA
Backside material	Veneer	Compliant Salvw 04	DА

Hardness (Brinell) value /	5 - 6 / 5 - 6	
range		
Warranty	30 years	
TECHNICAL PROPERTIES		
Moisture content	EN13183	7%±2%
Minimun Mean Density		>500 kg/m³
kg/m³		
Reaction To Fire	EN13501-1	Dfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 ppm
Breaking Strength N/mm²	EN1533	NPD
Thermal Conductivity	EN12664	0,11W/mK
Thermal Resistance R-Value	!	.11 (m2K/W)
Biological Durability	EN350-2	Class 1
CARB2		Compliant
Slip resistance	CEN/TS15676	NPD





DETAILED DESCRIPTION

DDODLIGT DETAIL O

Knots, cracks and uneven fillings is part of the design. These may change in apperance over the years.

Oil: This floor should be oiled immediately after installation.

Colour change: The colour matures over time.

Packages may contain start and stop boards.

Descriptions & Imagery

1 (2)

