



OAK VINGA

The pale grey hues featured in this 3-strip oak floor from the Götaland Collection reveal natural warm undertones resulting in a temperate expression. Occasional saw marks accentuate the floor's restored appearance. Each board is meticulously hand-scraped and carefully brushed to bring out the character of the grain and highlight the natural texture of the timber. Four-sided bevelling at the edges ensures a classic full plank look and feel.

PRODUCT DETAILS

| | |
|---------------------------|---|
| Article Number | 153N66EK03KW240 |
| EAN Code | 7393969042802 |
| Surface treatment | Oil This floor should be oiled immediately after installation. |
| Design features | Bevelled 4-sided, Handscraped, Brushed, Saw marks |
| Dimensions | 196 x 2419 mm |
| Weight per Package | 22.4 kg |
| Area per Package | 2.84 m ² |
| Area per pallet | 127.8 m ² |
| Package info | Packages may contain start and stop boards. |

DETAIL DESCRIPTION

Contains knots and all natural colour variations.

COLOUR CHANGE

The colour matures over time


FACTS

| | |
|-----------------------------|---------------------|
| Wood Species | Oak |
| Design | 3-strip |
| Grading | Dynamic |
| Range | Kährs Original |
| Collection | Götaland Collection |
| Resandable | 2-3 times |
| Natural/Stained | Stained |
| Brinell Value | 3,7 |
| Joint | Woodloc® 5S |
| Floor heating | Yes |
| Warranty | 30 years |
| Warranty US | 25 years |
| Wear-layer material | Hardwood |
| Wear Layer Thickness | 3.5 mm |
| Core material | Pine/Spruce/Alder |
| Backside material | Spruce |
| Thickness | 15 mm |
| Installation method | Floating, Glue-down |
| Surface Colour | Grey |


TECHNICAL PROPERTIES

| | | |
|--|--------------------------|--------------------------|
| Moisture content | EN13183 | 7%±2% |
| Minimum Mean Density kg/m³ | >500 kg/m ³ | |
| Reaction To Fire | EN13501-1 | Dfl-s1 |
| Formaldehyde Emission | EN717-1 | E1 |
| Content PCP | CEN/TR14823 | ≤ 5 x 10 ⁻⁶ n |
| Breaking Strength N/mm² | EN1533 | NPD |
| Thermal Conductivity | EN12664 | 0,14 W/mK |
| Thermal Resistance R-Value | .11 (m ² K/W) | |
| Biological Durability | EN350-2 | Class 1 |
| CARB2 | Compliant | |
| Slipperiness | CEN/TS15676 | NPD |


Other products in this collection



Oak Boda



Oak Backa



Oak Vinga



Oak Attebo



Oak Kilesand

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.