




ALE

With it's saturated, rich and warm nuances, this floor creates a generous and luxurious ambiance.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES			
Article Number	153N6CEKQ1KW240	Wood Species	Oak	Moisture	EN13183	7%±2%	
EAN Code	7393969041799	Design	3-strip	content			
Surface Treatment	Matt lacquer	Grading	Lively	Minimun Mean Density kg/m³ >500 kg/m³			
Refining Treatment	Brushed	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1	
Dimensions	200 x 2423 mm	Collection	Harmony Collection	Formaldehyde Emission	EN717-1	E1	
Weight per Package	23 kg	Natural/Stained	Stained				
Area per Package	2.9 m ²	Brinell Value	3,7	Content PCP	CEN/TR14823	≤ 5 x 10-6n	
Area per pallet	130.1 m ²	Joint	Woodloc® 5S	Breaking	EN1533	NPD	
Package info	Packages may contain start and stop boards.	Floor heating	Yes	N/mm² Thermal			
			25 years		EN12664	0,14 W/mK	
DETAIL DESCRIPTION		Wear-layer material	Hardwood	Conductivity			
All naturally occuring wood colour variations allowed, from light to dark brown. Sapwood will occur. The product includes large sound and black knots and cracks. Knots and cracks may vary in size and numbers.		Wear Layer Thickness	3.5 mm	Thermal Resistance R-Value		.11 (m2K/W)	
		Core material	Pine/Spruce lamella	Biological Durability	EN350-2	Class 1	
		Backside material	Spruce	CARB2		Compliant	
			15 mm	Slipperiness CEN/TS15676			
COLOUR CHANGE		Installation method	Floating, Glue-down				
Stained product - noticable color change over time.		Surface Colour	Warm brown				

Other products in this collection



CERTIFICATES









Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.