




OAK LECCO MATT 226

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	133BABEK15KW226	Wood Species	Oak	Moisture	EN13183	7%±2%
EAN Code	7393969047692	Design	3-strip	content		
Surface treatment	Matt lacquer	Grading	Variation	Minimun Mean	Minimun Mean Density kg/m³ >500 kg/m³	
Dimensions	188 x 2266 mm	Range	Kährs Avanti	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package	24.55 kg	Collection	Tres collection	Formaldehyde	EN717-1	E1
Area per Package	3.41 m²	Resandable	2-3 times	Emission		
Area per pallet	119.35 m ²	Natural/Stained	Natural	Content PCP	CEN/TR14823	3 ≤ 5 ppm
Package info	Packages may contain start and stop boards.	Brinell Value	3,7	Breaking	EN1533	NPD
		Joint	Woodloc® 5G	Strength N/mm²		
DETAIL DESCRIPTION		Floor heating	Yes	Thermal	EN12664	0,14 W/mK
Naturally occuring wood colour variations allowed, from light to dark brown. Will include sapwood. The product includes medium sound and black knots. Knots may vary in size and numbers. COLOUR CHANGE		Warranty	20 years	Conductivity		
		Warranty US	20 years	Thermal Resista	Thermal Resistance R-Value	
		Wear-layer material	Hardwood	Biological Durability	EN350-2	Class 1
		Wear Layer Thickness	2.6 mm	CARB2	CAPR2	
		Core material	Pine/Spruce/Alder	Slipperiness	CEN/TS15676	Compliant
Some muting of colour variation to medium, straw brown.		Thickness	13 mm	Silpperilless	CEN/13130/0	INFU
		Installation method	Floating, Glue-down			

Other products in this collection



CERTIFICATES

Oak Pima











Oak Erve









Oak Abetone

Oak Lecco

Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.