



## OAK ABETONE

Oak Abetone is a 3-strip floor with moderate colour variations and a white stain. May contain minor knots.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	133NABEK1VKW240	Wood Species	Oak	Moisture	EN13183	7%±2%
EAN Code	7393969034142	Design	3-strip	content	_	
Surface Treatment	Matt lacquer	Range	Kährs Avanti	Minimun Mean	Density kg/m <sup>3</sup>	>500 kg/m <sup>3</sup>
Dimensions	200 x 2423 mm	Collection	Tres collection	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package	24.5 kg	Natural/Stained	Stained	Formaldehyde Emission	EN717-1	E1
Area per Package	3.4 m <sup>2</sup>	Brinell Value	3,7			
Area per pallet	170 m²	Joint	Woodloc® 5G	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Package info	Packages may contain start and stop boards.	Floor heating	Yes	Breaking Strength N/mm²	EN1533	NPD
			20 years			
DETAIL DESCRIPTION		Wear-layer material	Hardwood	Thermal	EN12664	0,14 W/mK
Naturally occuring wood colour variations allowed, from light to dark brown. The product includes medium sound and black knots. Knots may vary in size and numbers.  COLOUR CHANGE		Wear Layer Thickness	2.6 mm	Conductivity		
		Core material	Pine/Spruce/Alder	Thermal Resistance R-Value		.09 (m2K/W)
			13 mm	Biological Durability	EN350-2	Class 1
		Installation method	Floating, Glue-down	CARB2		Compliant
Stained product - noticable color change over time.		_		Slipperiness	CEN/TS15676 NPD	
	0					

## Other products in this collection







Ash Ceriale



Ash Vaila



Oak Erve



Oak Abetone



Oak Lecco

## CERTIFICATES









**Descriptions & Imagery** 

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.