



OAK LECCO OILED

Oak Lecco is a 3-strip floor with moderate colour variations and it may contain minor knots.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	133NABEF0KW240	Wood Species	Oak	Moisture content	EN13183	7%±2%
EAN Code	7393969034197	Design	3-strip	Minimum Mean Density kg/m³ >500 kg/m³		
Surface Treatment	Oil This floor should be oiled immediately after installation.	Grading	Variation	Reaction To Fire	EN13501-1	Dfl-s1
		Range	Kährs Avanti	Formaldehyde Emission	EN717-1	E1
		Collection	Tres collection	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Dimensions	200 x 2423 mm	Natural/Stained	Natural	Breaking Strength N/mm²	EN1533	NPD
Weight per Package	24.5 kg	Brinell Value	3,7	Thermal Conductivity	EN12664	0,14 W/mK
Area per Package	3.4 m²	Joint	Woodloc® 5G	Thermal Resistance R-Value		.09 (m2K/W)
Package info	Packages may contain start and stop boards.	Floor heating	Yes	Biological Durability	EN350-2	Class 1
			20 years	CARB2		Compliant
		Wear-layer material	Hardwood	Slipperiness	CEN/TS15676	NPD
		Wear Layer Thickness	2.6 mm			
DETAIL DESCRIPTION	Naturally occuring wood colour variations allowed, from light to dark brown. Will include sapwood. The product includes medium sound and black knots. Knots may vary in size and numbers.	Core material	Pine/Spruce/Alder			
			13 mm			
		Installation method	Floating, Glue-down			
COLOUR CHANGE						
Some muting of colour variation to medium, straw brown.						

Other products in this collection



European Maple Gotha



Ash Ceriale



Ash Vaila



Oak Erve



Oak Abetone



Oak Lecco

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.