

OAK LIMESTONE

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	153N0BEK0WKW240	Wood Species	White Oak	Moisture	EN13183	7%±2%
EAN Code	7393969032629	Design	3-strip	content		
Surface Treatment	Matte finish	Grading	Lively	Minimun Mean Density kg/m ³ >500 kg/m ³		
Refining Treatment	Brushed	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1
Dimensions	7 7/8 x 95 3/8 "	Collection	Harmony Collection	Formaldehyde Emission	EN717-1	E1
Weight per Package	50.7 lbs	Resandable	2 times			
Area per Package	31.2 sqft	Natural/Stained	Stained	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Area per pallet	1400.4 sqft	Brinell Value	3,7	Breaking	EN1533	NPD
Package info	Packages may contain start and stop boards.	Joint	Woodloc® 5S	Strength N/mm²		
		Floor heating	Yes	Thermal	EN12664	0,14 W/mK
DETAIL DESCRIPTION		Warranty	30 years	Conductivity		
Naturally occuring wood colour variations allowed, from light to dark brown. Will include sapwood. The product includes medium sound and black knots. Knots may vary in size and numbers.		Warranty	25 years	Thermal Resistance R-Value .11 (.11 (m2K/W)
		Wear-layer material	Hardwood	Biological Durability	EN350-2	Class 1
		Wear Layer Thickness	1/8"	CARB2		Compliant
COLOR CHANGE		Core material	Pine/Spruce lamella	Slipperiness CEN/TS156		•
		Thickness	5/8"	Subbermess	CEIW/1515070	
Ctained are duct patie	able color change over time					

Stained product - noticable color change over time.

Installation method Surface Color

White

Floating, Glue-Down

Other products in this collection



Oak Limestone

Oak Lava

CERTIFICATES



Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.