




ZERO & GREEN 5312 CONCRETE

PRODUCT DETAILS



Reaction To Fire

TECHNICAL PROPERTIES EN13501-1 Cfl-s1 EN12664 Thermal Conductivity 0,22 W/mK Dimensional stability EN ISO 23999 < 0.2 % (50 °C/6 h) Colour fastness EN ISO 105-B02 ≥ 6 DS (>0.3) Slip resistance EN 13893 Slip resistance DIN 51130 R9 Statical electrical propensity EN 1815 < 2 kV (antistatic) Effect of castor chair EN 425 Suitable Resistance to bacteria and Good fungi













Other products in this collection



ZERO & GREEN 5322 Dusty




ZERO & GREEN 5364 Ambrosia



ZERO & GREEN 5312 Concrete



ZERO & GREEN 5304 Stone



ZERO & GREEN 5352 Blue Moon




ZERO & GREEN 5323 Morocco



ZERO & GREEN 5329 Sunbeam



ZERO & GREEN 5311 Silver Grey



ZERO & GREEN 5303 Pewter



ZERO & GREEN 5302 Cape Cod