




# MÖRE

A rustic product with a scraped, flowing surface that high enhances the structure in an natural way. The cold greys appear to have been worn down, revealing a warmer base.

## PRODUCT DETAILS

<b>Article Number</b>	151NCSEK03KW240
<b>Surface Treatment</b>	Oil
<b>Refining Treatment</b>	Bevelled 4-sided, Brushed, Handscraped
<b>Dimensions</b>	2420 x 187 x 15 mm
<b>Weight per Package</b>	22 kg
<b>Area per Package</b>	2.72 m <sup>2</sup>
<b>Area Per Board</b>	0.453 m <sup>2</sup>

## DETAIL DESCRIPTION

All naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes very large sound and black knots and cracks. Knots and cracks will be present in all sizes and numbers.

## COLOUR CHANGE

Stained product - noticable color change over time.

## CERTIFICATES

## FACTS

<b>Wood Species</b>	Oak
<b>Design</b>	1-strip
<b>Grading</b>	Dynamic
<b>Range</b>	Kährs Supreme
<b>Collection</b>	Småland Collection
<b>Natural/Stained</b>	Stained
<b>Brinell Value</b>	3,7
<b>Joint</b>	Woodloc® 5S
<b>Floor heating</b>	Yes
<b>Wear-layer material</b>	Hardwood
<b>Core material</b>	Pine/Spruce lamella
<b>Thickness</b>	15 mm
<b>Installation method</b>	Floating, Glue-down
<b>Surface Colour</b>	Earth Grey

## TECHNICAL PROPERTIES

<b>Moisture content</b>	EN13183	7%±2%
<b>Minimun Mean Density kg/m<sup>3</sup></b>		>500 kg/m <sup>3</sup>
<b>Reaction To Fire</b>	EN13501-1	Dfl-s1
<b>Formaldehyde Emission</b>	EN717-1	E1
<b>Content PCP</b>	CEN/TR14823	≤ 5 x 10 <sup>-6</sup> n
<b>Breaking Strength N/mm<sup>2</sup></b>	EN1533	NPD
<b>Thermal Conductivity</b>	EN12664	0,14 W/mK
<b>Thermal Resistance R-Value</b>		.11 (m2KW)
<b>Biological Durability</b>	EN350-2	Class 1
<b>CARB2</b>		Compliant

