

LRV



## OAK WISDOM

The OAK WISDOM floor's natural bronze color and subtle matt lacquer gives it a warm and inviting look. Each board's brushing and beveling process emphasizes the unique grain and texture, creating a tactile experience. The use of renewable natural oak adds to the flooring's sustainability, and its warmth and character make it a timeless choice for any space.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	141XADEK05KW195	Wood Species	Oak	Moisture	EN13183	7%±2%
EAN Code	7393969301688	Design	1-strip	content		
Surface Treatment	Matt lacquer	Grading	Dynamic	Minimun Mean Density kg/m³ >500 kg/m³		
Refining Treatment	Microbevelled 4-sided,	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1
	Brushed	Collection	Zen Collection	Formaldehyde Emission	EN717-1	E1
Dimensions	190 x 1900 mm	Natural/Stained	Natural			
Weight per Package	22.18 kg	Brinell Value	3,7	Content PCP	CEN/TR14823	3 ≤ 5 x 10-6n
Area per Package	2.88 m <sup>2</sup>	Joint	Woodloc® 5G	Breaking	EN1533	NPD
Area per pallet	129.6 m <sup>2</sup>	— Floor heating	Yes	Strength N/mm <sup>2</sup>		
Package info	Packages may contain start and stop boards.	Wear-layer material	Hardwood	Thermal Conductivity	EN12664	0,14 W/mK
		Wear Layer Thickness	2.7 mm			
		Core material	Pine/Spruce lamella	Biological Durability	EN350-2	Class 1
		Backside material	Veneer			
			14 mm			
		Installation method	Floating, Glue-down			

34

## Other products in this collection









OAK WISDOM

OAK HAPPINESS

OAK JOY OAK CALM



**OAK STRENGTH** 

## CERTIFICATES







## **Descriptions & Imagery**

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.