



STUDIO SMOKED OAK AB 11 MM

Smoked Oak AB is a clean dark brown oak with some colour variation and small knots with a matt finish.

PRODUCT DETAILS

Article Number	111PABEK0CKE050
EAN Code	7393969042291
Surface Treatment	Matt lacquer
Refining Treatment	Smoked
Dimensions	70 x 490 mm
Weight per Package	13.3 kg
Area per Package	2.1 m ²
Package info	Packages may contain start and stop boards.

DETAIL DESCRIPTION

Even colour with minor variations. The smoked design is likely to enhance the naturally occurring wood color variations and create further contrast between light and dark. Small sized knots in limited numbers allowed.

COLOUR CHANGE

Smoked product - noticable color change over time.

FACTS

Wood Species	Oak
Design	Pattern
Grading	Calm
Range	Kährs Master
Collection	Studio Collection
Natural/Stained	Natural
Brinell Value	3,7
Joint	Tongue & Groove
Floor heating	Yes
Wear-layer material	Hardwood
Wear Layer Thickness	4 mm
Core material	Birch Plywood
	11 mm
Installation method	Glue-down
Surface Colour	Dark Brown

TECHNICAL PROPERTIES

Moisture content	EN13183	7%±2%
Minimum Mean Density kg/m ³	>500 kg/m ³	
Reaction To Fire	EN13501-1	Cfl-s1
Formaldehyde Emission	EN717-1	E1
Content PCP	CEN/TR14823	≤ 5 x 10 ⁻⁶ n
Breaking Strength N/mm ²	EN1533	NPD
Thermal Conductivity	EN12664	0,14 W/mK
Thermal Resistance R-Value	.08 (m2K/W)	
Biological Durability	EN350-2	Class 1
CARB2	Compliant	
Slipperiness	CEN/TS15676	NPD

Other products in this collection



Studio Oak AB White 11 mm



Studio Smoked Oak AB 11 mm



Studio Oak AB 11 mm

Descriptions & Imagery

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.