

## OAK PORTOFINO

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	152N38EK0VKW240	Wood Species	White Oak	Moisture	EN13183	7%±2%
EAN Code	7393969026987	Design	2-strip	content		
Surface Treatment	Matte finish	Grading	Variation	Minimun Mean Density kg/m <sup>3</sup> >500 kg/m <sup>3</sup>		
Dimensions	7 7/8 x 95 3/8 "	Range	Kährs Original	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package	50.7 lbs	Collection	Sand Collection	Formaldehyde	EN717-1	E1
Area per Package	31.3 sqft	Resandable	2 times	Emission		
Area per pallet	1409.5 sqft	Natural/Stained	Stained	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Package info	Packages may contain start and stop boards.	Brinell Value	3,7	Breaking Strength N/mm²	EN1533	NPD
		Joint	Woodloc® 5S			
DETAIL DESCRIPTION		Floor heating	Yes	Thermal	EN12664	0,14 W/mK
Naturally occuring wood colour variations allowed, from light to dark brown. Will include sapwood. The product includes medium sound and black knots. Knots may vary in size and numbers.		Warranty	30 years	Conductivity		
		Warranty	25 years	Thermal Resista	Thermal Resistance R-Value	
		Wear-layer material	Hardwood	Biological Durability	EN350-2	Class 1
		Wear Layer Thickness	1/8"	CARB2		Compliant
COLOR CHANGE Core material		Core material	Pine/Spruce/Alder	Slipperiness	CEN/TS15676	•
Stained product - noticable color change over time.		Thickness	5/8"	Subbermess	CEN/1313070	
		Installation method	Floating, Glue-Down			

White

37

Surface Color

LRV

AB GUSTAF KÄHR | www.kahrs.com | © Kährs 2023

## Other products in this collection



Oak Portofino

## CERTIFICATES



## **Descriptions & Imagery**

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.