



# OAK VERONA

## PRODUCT DETAILS

<b>Article Number</b>	152N38EK09KW 0
<b>EAN Code</b>	7393969025171
<b>Surface Treatment</b>	Matte finish
<b>Dimensions</b>	95 3/8 x 7 7/8 x 5/8"
<b>Weight per Package</b>	50.70 lbs
<b>Area per Package</b>	31.20 sqft
<b>Area per pallet (m²)</b>	1,400.40 sqft
<b>Package info</b>	Packages may contain start and stop boards.

## DETAIL DESCRIPTION

Naturally occurring wood colour variations allowed, from light to dark brown. Sapwood may occur. The product includes medium sound and black knots. Knots may vary in size and numbers.

## COLOR CHANGE

Some muting of colour variation to medium, straw brown.

## FACTS

<b>Wood Species</b>	White Oak
<b>Design</b>	2-strip
<b>Grading</b>	Variation
<b>Range</b>	Kährs Original
<b>Collection</b>	European Naturals Collection
<b>Resandable</b>	2 times
<b>Natural/Stained</b>	Natural
<b>Brinell Value</b>	3,7
<b>Joint</b>	Woodloc® 5S
<b>Floor heating</b>	Yes
	30 years
<b>Wear-layer material</b>	Hardwood
<b>Wear-layer thickness</b>	1/8"
<b>Core material</b>	Pine/Spruce lamella
<b>Thickness</b>	5/8"
<b>Installation method</b>	Glue-Down, Floating

## TECHNICAL PROPERTIES

<b>Moisture content</b>	EN13183	7%±2%
<b>Minimum Mean Density kg/m³</b>	>500 kg/m³	
<b>Reaction To Fire</b>	EN13501-1	Dfl-s1
<b>Formaldehyde Emission</b>	EN717-1	E1
<b>Content PCP</b>	CEN/TR14823	≤ 5 x 10-6n
<b>Breaking Strength N/mm²</b>	EN1533	NPD
<b>Thermal Conductivity</b>	EN12664	0,14 W/mK
<b>Thermal Resistance R-Value</b>	.11 (m2K/W)	
<b>Biological Durability</b>	EN350-2	Class 1
<b>CARB2</b>	Compliant	



**Descriptions & Imagery**

*All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.*