

TECHNICAL DATA KÄHRS LUXURY TILES

DRY BACK WOOD AND STONE

DRY BACK HERRINGBONE

wear layer 0.7 mm



Dry back Stone 457 x 457 x 2.5 x 0.7 mm
5.01 m²/box



Dry back Herringbone 102 x 457 x 2.5 x 0.7 mm
2.78 m²/box



Dry back Stone 305 x 609 x 2.5 x 0.7 mm
2.58 m²/box






Dry back Wood 228.6 x 1219.2 x 2.5 x 0.7 mm
3.9 m²/box

PRODUCT












Dry back	EN ISO 10582	Luxury Vinyl Tile
Application	EN ISO 10874	23/34/43



SPECIFICATION

Thickness		EN ISO 24337	2.5 mm
Weight		EN ISO 24342	4.2 kg/m ²
Wear layer		EN ISO 24346	0.7 mm

PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, FloorScore, A+
Fire resistance	 EN 13501-1	B _{fl} -s1
Residual indentation	 EN ISO 24343-1	≤ 0.05 mm
Dimensional stability	 EN ISO 23999	< 0.1%
Colour fastness	 EN ISO 105-B02	≥ 6
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R10
Electrical propensity	 EN 1815	< 2 kV (antistatic)
Wear resistance	 EN 660-2	< 2.0 mm ³ (Group T)
Chemical resistance	 EN ISO 26987	Pass with good results
Thermal resistance	 EN 12664:2001	0.011 m ² K/W
Effect of castor chair	 EN 425	Suitable
Underfloor heating		Ok (max +27 °C)
Resistance to bacteria and fungi		Good