

# TECHNICAL DATA

## KÄHRS LUXURY TILES

### DRY BACK XPRESSION



7" x 48" x 0.08"

#### PRODUCT

Xpression	EN 14565	PVC- and plasticizer-free Enomer® plank
Application	EN ISO 10874	23/34/43



#### SPECIFICATION

Thickness	EN ISO 24346	~0.08" (2.0 mm)
Weight	EN ISO 23997	~0.70 lbs / sq ft (3400 g/m <sup>2</sup> )
Plank size	EN ISO 24342	7" x 48" x 0.08" (177.8 x 1219.2 x 2 mm)

#### PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, Floorscore, Austrian Ecolabel
Electrostatic Propensity	AATCC 134	< 2.0 kV
Slip Resistance DCOF (Wet)	ANSI B 101.3	Acceptable
Slip Resistance DCOF (Dry & Wet)	ASTM C 1028	≥ 0.7 Dry / Wet
Abrasion Resistance w weight loss	ASTM D 4060	~ 0.05 g
Castor Chair Test 25.000 cycles	EN 425	Pass
Critical Radiant Flux	ASTM E 648	≥ 0.45 W/cm <sup>2</sup> Class 1
Smoke Density	ASTM E 662	≤ 450 Flaming & Non-flaming
Flexibility	ASTM F 137	Pass (1" mandrel)
Resistance to Heat	ASTM F 1514	Pass
Resistance to Light	ASTM F 1515	Pass
Short Term Indentation	ASTM F 1914	< 0.005" (6%)
Chemical Resistance	ASTM F 925	Excellence
Static Load Limit	ASTM F 970	Pass
Static Load Limit	ASTM F 970 Mod	2000 psi
Resistance to bacteria and fungi	EN 846	Good



COLLECTION  
KÄHRS LUXURY TILES

DRY BACK XPRESSION

7" x 48" x 0,08"



1511 Xpression Almond



1504 Xpression Smoked



1512 Xpression Dune




1514 Xpression Chestnut



1503 Xpression Natural



1515 Xpression Charcoal



1513 Xpression Hazel




1501 Xpression Warm Grey



1516 Xpression Golden Oak




1502 Xpression Cool Grey



1519 Xpression American Cherry



1505 Xpression Dark Grey



1517 Xpression French Walnut