

# TECHNICAL DATA KÄHR'S LUXURY TILES

DRY BACK WOOD AND STONE

DRY BACK HERRINGBONE

wear layer 0.7 mm



**Dry back Stone** 457 x 457 x 2.5 x 0.7 mm  
5.01 m<sup>2</sup>/box



**Dry back Herringbone** 102 x 457 x 2.5 x 0.7 mm  
2.78 m<sup>2</sup>/box



**Dry back Stone** 305 x 609 x 2.5 x 0.7 mm  
2.58 m<sup>2</sup>/box






**Dry back Wood** 228.6 x 1219.2 x 2.5 x 0.7 mm  
3.9 m<sup>2</sup>/box

## PRODUCT












Dry back	EN ISO 10582	Luxury Vinyl Tile
Application	EN ISO 10874	23/34/43



## SPECIFICATION

Thickness		EN ISO 24337	2.5 mm
Weight		EN ISO 24342	4.2 kg/m <sup>2</sup>
Wear layer		EN ISO 24346	0.7 mm

## PRODUCT PROPERTIES

PROPERTY	TEST METHOD	RESULT
Indoor air certifications		M1, FloorScore, A+
Fire resistance	 EN 13501-1	Bfl-s1
Residual indentation	 EN ISO 24343-1	≤ 0.05 mm
Dimensional stability	 EN ISO 23999	< 0.1%
Colour fastness	 EN ISO 105-B02	≥ 6
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R10
Electrical propensity	 EN 1815	< 2 kV (antistatic)
Wear resistance	 EN 660-2	< 2.0 mm <sup>3</sup> (Group T)
Chemical resistance	 EN ISO 26987	Pass with good results
Thermal resistance	 EN 12664:2001	0.011 m <sup>2</sup> K/W
Effect of castor chair	 EN 425	Suitable
Underfloor heating		Ok (max +27 °C)
Bacterial growth		Does not act as substrate

