Test No: 146821



Phone: 706-278-3013

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722

Fax: 706-272-7057 •

E-mail: info@ittslab.com

Test Report

Customer: UPOFLOOR

August 25, 2014

Subject: One sample of vinyl floor covering submitted by the customer and identified as below.

Sample Identification: Upofloor Zero 5703

Contract Sheet

Date of Manufacturing: 25th June 2014

Test Method Conducted ASTM F 1515 Standard Test Method for Measuring Light Stability of Resilient Vinyl Flooring by Color Change

Scope:

This method covers a procedure for determining the resistance of resilient vinyl floor covering to color change from exposure to light over a specified period of time.

Specified Apparatus:

Atlas CI5000

Specified time:

300 AFU's

Light Source:

Water Cooled Xenon ARC

Test Results	ΔE
Average	1.667

President L. Kent Suddeth

Our letters and reports are for the exclusive use of the oustoner to whom they are addressed, and their communication to any others or the use of the name of independent Textile Testing Sarvice, Inc., must receive out prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualifies of advertising to the general products. The apports and letters and the name of independent Textire Testing Sarvice, Inc., are not to be used under any circumstances in advertising to the general public.