



TEST REPORT

DATE: 10-25-2017

Page 1 of 1

TEST NUMBER: 0241320

CLIENT	UPOFLOOR
---------------	----------

TEST METHOD CONDUCTED	ASTM D2047 James Machine - Coefficient of Friction on Flooring Material
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Zero Tiles 5112/9501
LOT NUMBER	25617
CONSTRUCTION	Vinyl Tile

GENERAL PRINCIPLE

This test was used to measure the relative static coefficient of friction by using the James Machine.

TEST RESULTS

TEST ENVIRONMENT	69° F 50% Relative Humidity
-------------------------	-----------------------------

Sensor Materials	Dry	Wet (25 mls of H ₂ O)
Standard Neolite	0.94	0.91

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.