



TEST REPORT

DATE: 10-25-2017

Page 1 of 1

TEST NUMBER: 0241320

CLIENT	UPOFLOOR
---------------	----------

TEST METHOD CONDUCTED	ASTM F2199 Test Method for Determining Dimensional Stability of Resilient Floor Tile after Exposure to Heat
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Zero Tiles 5112/9501
LOT NUMBER	25617
CONSTRUCTION	Vinyl Tile

GENERAL PRINCIPLE

This test method is intended for use in determining the linear change of resilient flooring after being exposed to heat. The dimensional change over 12 inches is reported as the dimensional stability.

TEST RESULTS

REPLICATE	IDENTIFICATION	RESULT
#1	Length	-0.010 Inch per 12 inches (-0.08%)
	Width	-0.002 Inch per 12 inches (-0.02%)
#2	Length	-0.004 Inch per 12 inches (-0.03%)
	Width	-0.002 Inch per 12 inches (-0.02%)
#3	Length	-0.009 Inch per 12 inches (-0.07%)
	Width	-0.003 Inch per 12 inches (-0.02%)

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical of similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.