

# TECHNICAL DATA

## ZERO & GREEN





### ENOMER® CONTRACT SHEET FLOORING

#### PRODUCT















Zero & GREEN	EN 14565	PVC- and plasticizer-free Enomer® flooring
Application	EN ISO 10874	23/34/43



#### SPECIFICATION


Thickness	 EN ISO 24346	2.0 mm
Weight	 EN ISO 23997	3100 g/m <sup>2</sup>
Roll length	 EN ISO 24341	10 - 25 m
Width	 EN ISO 24341	145 cm

#### PRODUCT PROPERTIES


PROPERTY	TEST METHOD	RESULT
Fire resistance	 EN 13501-1	C <sub>fl</sub> -s1
Residual indentation	 EN ISO 24343-1 (2.5 h)	ca. 0.03 mm
Slip resistance	 EN 13893 DIN 51130	DS (> 0.3) R9
Electrical propensity	 EN 1815	≤ 2 kV (antistatic)
Wear and scratch resistance	 EN 660-2 ISO 5470-1	≤ 2.0 mm <sup>3</sup> (Class T) 0.05 g/1000 cycles
Effect of castor chair	 EN 425	Suitable
Dimensional stability	 EN ISO 23999 (50 °C/6 h)	< 0.2%
Colour fastness	 EN ISO 105-B02	≥ 6
Flexibility	 EN ISO 24344 Method A	10 mm
Chemical Resistance	 EN ISO 26987	Excellent
Underfloor heating	 EN ISO 26987	Suitable (max. +28 °C)
Insulation resistance	 EN 1081	> 100 GΩ
Watertightness	 EN 13553 Annex A	Pass
Thermal conductivity	 EN 12667	0.22 W/mK
Tensile strength of seam	EN 684	> 400 N / 50 mm
Resistance to bacteria and fungi	ISO 846	Good

**Kährs**

COLLECTION  
**ZERO & GREEN**  
ENOMER® CONTRACT SHEET FLOORING



5311 SILVER GREY




5312 CONCRETE

NCS S 3000-N

NCS S 3502-Y




5302 CAPE COD



5303 PEWTER

NCS S 2500-N

NCS S 4500-N



5304 STONE GREY

NCS S 6000-N




5322 DUSTY

NCS S 2005-Y30R




5364 AMBROSIA



5352 BLUE MOON


NCS S 2005-G30Y

NCS S 5020-R80B



5323 MOROCCO

NCS S 4010-Y30R



5329 SUNBEAM

NCS S 2030-Y20R